

ABSTRACT

Provided is a silicon carbide epitaxial wafer which is formed on a substrate that is less than 1° off from the {0001} surface of silicon carbide having an α -type
5 crystal structure, wherein the crystal defects in the SiC epitaxial wafer are reduced while the flatness of the surface thereof is improved.